

## Cresset Powers Cress-Alon™ NE2740 4% Nano Clay Loaded, 2.7 r.v. Compounding Grade Nylon 6, Dry As Molded

Category : Polymer , Thermoplastic , Nylon , Nylon 6

### Material Notes:

Low density, high rigidity, high heat distortion temperature, high retention of mechanical properties under humid conditions, flame retardant, recyclable and environmentally friendly, less glass fiber required to achieve same properties as non-nano nylon, low opacifying property, excellent surface smoothness and glossiness, low water absorption, excellent moldability, high crystallinity, good dimensional stability, good barrier properties to gas, solvent, and UV, high resistance to oil, greases, hydrocarbons, and chemicals, and may help flame retardant properties with anti-dripping. Information provided by Cresset Powers Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cresset-Powers-Cress-Alon-NE2740-4-Nano-Clay-Loaded-27-rv-Compounding-Grade-Nylon-6-Dry-As-Molded.php](http://www.lookpolymers.com/polymer_Cresset-Powers-Cress-Alon-NE2740-4-Nano-Clay-Loaded-27-rv-Compounding-Grade-Nylon-6-Dry-As-Molded.php)

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in <sup>3</sup>	ASTM D792
Viscosity Measurement	2.7	2.7	Relative Viscosity
Melt Flow	48.3 g/10 min @Load 5.00 kg, Temperature 235 °C	48.3 g/10 min @Load 11.0 lb, Temperature 455 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	103 MPa	14900 psi	ASTM D638
Tensile Strength, Yield	103 MPa	14900 psi	ASTM D638
Elongation at Break	1.4 %	1.4 %	ASTM D638
Elongation at Yield	1.4 %	1.4 %	ASTM D638
Flexural Yield Strength	163 MPa	23600 psi	ASTM D790
Flexural Modulus	4.50 GPa	653 ksi	ASTM D790
Izod Impact, Notched	0.300 J/cm	0.562 ft-lb/in	ASTM D256, Notch

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	ASTM DSC

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China