

Cresset Powers Cress-Alon™ NF3040 4% Nano Clay Loaded, 3.0 r.v. Film Grade Nylon 6, Dry As Molded

Category : Polymer , Film , Thermoplastic , Nylon , Nylon 6

Material Notes:

Low density, high rigidity, high heat distortion temperature, high retention of mechanical properties under humid conditions, flame retardant, recyclable and environmentally friendly, less glass fiber required to achieve same properties as non-nano nylon, low opacifying property, excellent surface smoothness and glossiness, low water absorption, excellent moldability, high crystallinity, good dimensional stability, good barrier properties to gas, solvent, and UV, high resistance to oil, greases, hydrocarbons, and chemicals, and may help flame retardant properties with anti-dripping. Information provided by Cresset Powers Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cresset-Powers-Cress-Alon-NF3040-4-Nano-Clay-Loaded-30-rv-Film-Grade-Nylon-6-Dry-As-Molded.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	ASTM D792
Viscosity Measurement	3.0	3.0	Relative Viscosity
Melt Flow	8.9 g/10 min @Load 5.00 kg, Temperature 230 °C	8.9 g/10 min @Load 11.0 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	90.0 MPa	13100 psi	ASTM D638
Elongation at Break	3.2 %	3.2 %	ASTM D638
Elongation at Yield	2.0 %	2.0 %	ASTM D638
Flexural Yield Strength	155 MPa	22500 psi	ASTM D790
Flexural Modulus	4.20 GPa	609 ksi	ASTM D790
Izod Impact, Notched	0.270 J/cm	0.506 ft-lb/in	ASTM D256, Notch

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	ASTM DSC

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China