

## Custom Resins Norpex® GF2 PPE (Polyphenylene Ether), 20% Glass Filled (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polyphenylene Ether, 20% Glass Filled

### Material Notes:

Properties for dry as molded samples.Data provided by the manufacturer

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Custom-Resins-Norpex-GF2-PPE-Polyphenylene-Ether-20-Glass-Filled-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Custom-Resins-Norpex-GF2-PPE-Polyphenylene-Ether-20-Glass-Filled-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	97.0 MPa	14100 psi	ASTM D638
Flexural Yield Strength	124 MPa	18000 psi	ASTM D790
Flexural Modulus	4.80 GPa	696 ksi	ASTM D790
Izod Impact, Notched	1.10 J/cm	2.06 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	141 °C	286 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China