

Cytec EN-2534 (Conap) Potting and Encapsulation Adhesive

Category : Polymer , Adhesive , Thermoset , Polyurethane, TS , Thermoset Polyurethane, Adhesive

Material Notes:

Polyurethane Potting and Encapsulating Systems Conathane® EN-2500 series polyurethane potting and encapsulating systems from Cytec have varying degrees of worklife, viscosity and hardness for many specific potting and encapsulating applications such as modules, strain-sensitive components, transformers, and coils. All 2500 series systems exhibit excellent performance when exposed to adverse environments and temperature ranges between -55°C and +130°C. Cytec (Conap) EN-2534 Potting and Encapsulation Adhesive Passes Thermal Shock Test (10 Cycles, -65°C to 130°C) Non-Nutrient Fungus Resistance (MIL-STD-810B) Mix Ratio: 20/100 (by Weight)

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cytec-EN-2534-Conap-Potting-and-Encapsulation-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in ³	Cured
Water Absorption	0.15 %	0.15 %	24 hours
Water Absorption at Saturation	0.0045 %	0.0045 %	30 Days
Viscosity	2200 cP @Temperature 25.0 °C	2200 cP @Temperature 77.0 °F	
Linear Mold Shrinkage	0.0065 cm/cm	0.0065 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	50 - 55	50 - 55	
Tensile Strength, Ultimate	13.6 MPa	1970 psi	
Elongation at Break	60 %	60 %	

Thermal Properties	Metric	English	Comments
CTE, linear	150 µm/m-°C @Temperature 20.0 °C	83.3 µin/in-°F @Temperature 68.0 °F	
Thermal Conductivity	0.188 W/m-K	1.30 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	130 °C	266 °F	
Minimum Service Temperature, Air	-55.0 °C	-67.0 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	<= 3.40e+13 ohm-cm	<= 3.40e+13 ohm-cm	

Surface Resistance Electrical Properties	1.50e+13 ohm Metric	1.50e+13 ohm English	Comments
Dielectric Constant	4.1 @Frequency 1000 Hz	4.1 @Frequency 1000 Hz	
Dielectric Strength	23.0 kV/mm @Thickness 1.59 mm	584 kV/in @Thickness 0.0625 in	
Dissipation Factor	0.049 @Frequency 1000 Hz	0.049 @Frequency 1000 Hz	
Arc Resistance	>= 120 sec	>= 120 sec	

Processing Properties	Metric	English	Comments
Cure Time	120 min @Temperature 100 °C	2.00 hour @Temperature 212 °F	
	960 min @Temperature 80.0 °C	16.0 hour @Temperature 176 °F	
	10080 min @Temperature 25.0 °C	168.0 hour @Temperature 77.0 °F	
Pot Life	15.0 - 20.0 min @Temperature 25.0 °C	15.0 - 20.0 min @Temperature 77.0 °F	1 lbm

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China