

## Cytec Thornel® T-50 3K Carbon Fiber, Polyacrylonitrile (PAN) Precursor

Category : Carbon , Carbon Fiber , Other Engineering Material , Composite Fibers

### Material Notes:

Data provided by the manufacturer, Amoco Performance Products, Inc. Continuous length, high strength, high modulus fiber made from a polyacrylonitrile precursor. The fiber surface has been treated to increase the interlaminar shear strength in a resin matrix composite. 3000 filaments/strand, 99+% carbon assay, 6.5 µm filament diameter, 5.5 m/g yield, 16 tpm twist (also available untwisted), 0.1 mm<sup>2</sup> fiber area in yarn cross section. Thornel® products were sold by Amoco and are now owned by Cytec.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cytec-Thornel-T-50-3K-Carbon-Fiber-Polyacrylonitrile-PAN-Precursor.php](http://www.lookpolymers.com/polymer_Cytec-Thornel-T-50-3K-Carbon-Fiber-Polyacrylonitrile-PAN-Precursor.php)

Physical Properties	Metric	English	Comments
Density	1.81 g/cc	0.0654 lb/in <sup>3</sup>	
Specific Surface Area	0.45 m <sup>2</sup> /g	0.45 m <sup>2</sup> /g	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	2900 MPa	421000 psi	
Elongation at Break	0.60 %	0.60 %	
Modulus of Elasticity	390 GPa	56600 ksi	In Tension

Thermal Properties	Metric	English	Comments
CTE, linear	-1.15 µm/m-°C	-0.639 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	70.0 W/m-K	486 BTU-in/hr-ft <sup>2</sup> -°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000950 ohm-cm	0.000950 ohm-cm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China