

## Cytec Thornel® T-650/35 6K Carbon Fiber, Polyacrylonitrile (PAN) Precursor

Category: Carbon, Carbon Fiber, Other Engineering Material, Composite Fibers

## **Material Notes:**

Data provided by the manufacturer, Amoco Performance Products, Inc.Continuous length, high strength, high modulus fiber made from a polyacrylonitrile precursor. The fiber surface has been treated to increase the interlaminar shear strength in a resin matrix composite.6000 filaments/strand, 94% carbon assay, 6.8 µm filament diameter, 2.56 m/g yield, 0 tpm twist (also available twisted), 0.22 mm² fiber area in yarn cross section.Thornel® products were sold by Amoco and are now owned by Cytec.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Cytec-Thornel-T-65035-6K-Carbon-Fiber-Polyacrylonitrile-PAN-Precursor.php

Physical Properties	Metric	English	Comments
Density	1.77 g/cc	0.0639 lb/in³	
Specific Surface Area	0.50 m²/g	0.50 m²/g	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	4550 MPa	660000 psi	
Elongation at Break	1.75 %	1.75 %	
Modulus of Elasticity	241 GPa	35000 ksi	In Tension

Thermal Properties	Metric	English	Comments
CTE, linear	-0.500 μm/m-°C	-0.278 μin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	14.0 W/m-K	97.2 BTU-in/hr-ft <sup>2</sup> -°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00149 ohm-cm	0.00149 ohm-cm	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China