

DSM Akulon® K125 PA6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Low Viscosity

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Akulon-K125-PA6.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	dry; ISO 1183
Water Absorption	9.5 %	9.5 %	Sim. To ISO 62
Moisture Absorption	2.50 %	2.50 %	Sim. To ISO 62
Viscosity Test	152 cm ³ /g	152 cm ³ /g	Viscosity Number; ISO 307, 1157, 1628

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	10°C/min; ISO 11357-1/-3

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China