

## DSM Akulon® K224-G3 Nylon 6- 15% Glass Reinforced (European and Asian Grade) (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 20% Glass Fiber Filled

### Material Notes:

The Akulon® product portfolio is engineered for optimum performance to suit different processing techniques and end use markets. Akulon Nylon 6 is used for extrusion applications including barrier film, stock shapes, convoluted tubes, and monofilament. Akulon XP is a high-productivity, high-performance PA6 grade for film extrusion processes. Medium viscosity, unreinforced or reinforced Akulon grades are used for various injection molding and blow molding applications. Akulon® Ultraflow® is a high-productivity, high-performance PA6 family for molding processes. Key applications for Akulon: Automotive: Intake manifold, Engine, Powertrain, Airbag containers, Exterior trim, Interior trim, Electrical components and connectors Consumer durables: Power tools, Lawn and garden tools, Small appliances, Sports and leisure equipment, Furniture, Industrial Goods, Transportation E&E: Low voltage switch gear/power distribution, Lighting, Power connectors Film: Specialty and barrier films Information provided by DSM.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DSM-Akulon-K224-G3-Nylon-6-15-Glass-Reinforced-European-and-Asian-Grade-Dry.php](http://www.lookpolymers.com/polymer_DSM-Akulon-K224-G3-Nylon-6-15-Glass-Reinforced-European-and-Asian-Grade-Dry.php)

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in <sup>3</sup>	ISO 1183
Water Absorption	7.6 %	7.6 %	Sim. to ISO 62
Moisture Absorption at Equilibrium	2.3 %	2.3 %	Humidity Absorption; Sim. to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	130 MPa	18900 psi	ISO 527-1/-2
Elongation at Break	3.5 %	3.5 %	ISO 527-1/-2
Tensile Modulus	6.00 GPa	870 ksi	ISO 527-1/-2
Charpy Impact Unnotched	4.50 J/cm <sup>2</sup>	21.4 ft-lb/in <sup>2</sup>	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	5.00 J/cm <sup>2</sup>	23.8 ft-lb/in <sup>2</sup>	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.700 J/cm <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	30.0 µm/m-°C Metric	16.7 µin/in-°F English	Comments
CTE, linear, Parallel to Flow	@Temperature 20.0 °C	@Temperature 68.0 °F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	80.0 µm/m-°C @Temperature 20.0 °C	44.4 µin/in-°F @Temperature 68.0 °F	ISO 11359-1/-2
Melting Point	220 °C	428 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	ISO 75-1/-2
UL RTI, Electrical	65.0 °C @Thickness 1.50 mm	149 °F @Thickness 0.0591 in	UL746B
	65.0 °C @Thickness 0.750 mm	149 °F @Thickness 0.0295 in	UL746B
UL RTI, Mechanical with Impact	65.0 °C @Thickness 0.750 mm	149 °F @Thickness 0.0295 in	UL746B
	65.0 °C @Thickness 1.50 mm	149 °F @Thickness 0.0591 in	UL746B
UL RTI, Mechanical without Impact	65.0 °C @Thickness 1.50 mm	149 °F @Thickness 0.0591 in	UL746B
	65.0 °C @Thickness 0.750 mm	149 °F @Thickness 0.0295 in	UL746B
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	IEC 60695-11-10
	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Dielectric Constant	3.5 @Frequency 100 Hz	3.5 @Frequency 100 Hz	IEC 60250
	4.7 @Frequency 1e+6 Hz	4.7 @Frequency 1e+6 Hz	IEC 60250

Dielectric Strength Electrical Properties	35.0 kV/mm Metric	889 kV/in English	IEC 60243-1 Comments
Dissipation Factor	0.0055 @Frequency 100 Hz	0.0055 @Frequency 100 Hz	IEC 60250
	0.018 @Frequency 1e+6 Hz	0.018 @Frequency 1e+6 Hz	IEC 60250
Comparative Tracking Index	>= 600 V	>= 600 V	PLC 0; UL 746A

Descriptive Properties	Value	Comments
Injection molding	Yes	
Release Agent	Yes	
With Fillers	Yes	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China