

## DSM Akulon® K224-TPG3 Impact Modified Nylon 6- 15% Glass Reinforced (European Grade) (Cond) (discontinued \*\*)&

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 20% Glass Fiber Filled

### Material Notes:

The Akulon® product portfolio is engineered for optimum performance to suit different processing techniques and end use markets. Akulon Nylon 6 is used for extrusion applications including barrier film, stock shapes, convoluted tubes, and monofilament. Akulon XP is a high-productivity, high-performance PA6 grade for film extrusion processes. Medium viscosity, unreinforced or reinforced Akulon grades are used for various injection molding and blow molding applications. Akulon® Ultraflow® is a high-productivity, high-performance PA6 family for molding processes. Key applications for Akulon: Automotive: Intake manifold, Engine, Powertrain, Airbag containers, Exterior trim, Interior trim, Electrical components and connectors Consumer durables: Power tools, Lawn and garden tools, Small appliances, Sports and leisure equipment, Furniture, Industrial Goods, Transportation E&E: Low voltage switch gear/power distribution, Lighting, Power connectors Film: Specialty and barrier films Information provided by DSM.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DSM-Akulon-K224-TPG3-Impact-Modified-Nylon-6-15-Glass-Reinforced-European-Grade-Cond-ndiscontinued-.php](http://www.lookpolymers.com/polymer_DSM-Akulon-K224-TPG3-Impact-Modified-Nylon-6-15-Glass-Reinforced-European-Grade-Cond-ndiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in <sup>3</sup>	(DAM); ISO 1183
Water Absorption	6.8 %	6.8 %	DAM; Sim. to ISO 62
Moisture Absorption at Equilibrium	2.0 %	2.0 %	Humidity Absorption (DAM); Sim. to ISO 62

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	IEC 60093
Dielectric Constant	4.5	4.5	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	14	14	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	20.0 kV/mm	508 kV/in	IEC 60243-1
Dissipation Factor	0.12	0.12	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dissipation Factor	0.15	0.15	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	500 V	500 V	IEC 60112

Electrical Properties	Metric	English	Comments
Descriptive Properties		Value	Comments
High impact or impact modified		Yes	
Injection molding		Yes	
Release Agent		Yes	
With Fillers		Yes	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China