

DSM Akulon® S223-E Nylon 66 (European and Asian Grade) (Cond) (discontinued **)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

The Akulon® product portfolio is engineered for optimum performance to suit different processing techniques and end use markets. Akulon Nylon 6 is used for extrusion applications including barrier film, stock shapes, convoluted tubes, and monofilament. Akulon XP is a high-productivity, high-performance PA6 grade for film extrusion processes. Medium viscosity, unreinforced or reinforced Akulon grades are used for various injection molding and blow molding applications. Akulon® Ultraflow® is a high-productivity, high-performance PA6 family for molding processes. Key applications for Akulon: Automotive: Intake manifold, Engine, Powertrain, Airbag containers, Exterior trim, Interior trim, Electrical components and connectors Consumer durables: Power tools, Lawn and garden tools, Small appliances, Sports and leisure equipment, Furniture, Industrial Goods, Transportation E&E: Low voltage switch gear/power distribution, Lighting, Power connectors Film: Specialty and barrier films Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Akulon-S223-E-Nylon-66-European-and-Asian-Grade-Cond-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	(DAM); ISO 1183
Water Absorption	8.5 %	8.5 %	DAM; Sim. to ISO 62
Moisture Absorption at Equilibrium	2.3 %	2.3 %	Humidity Absorption (DAM); Sim. to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.0 MPa	8700 psi	ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	ISO 527-1/-2
Elongation at Yield	20 %	20 %	ISO 527-1/-2
Tensile Modulus	1.50 GPa	218 ksi	ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Notched	NB	NB	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Tensile Creep Modulus, 1 hour Mechanical Properties	3400 MPa Metric	493000 psi English	ISO 899-1 Comments
--	--------------------	-----------------------	-----------------------

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	10°C/min (DAM); ISO 11357-1/-3

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093
Dielectric Constant	4.0	4.0	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	10	10	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	20.0 kV/mm	508 kV/in	IEC 60243-1
Dissipation Factor	0.10	0.10	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.14	0.14	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	600 V	600 V	IEC 60112

Descriptive Properties	Value	Comments
Injection molding	Yes	
Lubricants	Yes	
Without Fillers	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China