

DSM Akulon® Ultraflow™ K-FHG0 Nylon 6-50% Glass Reinforced (European Grade) (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 50% Glass Fiber Filled

Material Notes:

The Akulon® product portfolio is engineered for optimum performance to suit different processing techniques and end use markets. Akulon Nylon 6 is used for extrusion applications including barrier film, stock shapes, convoluted tubes, and monofilament. Akulon XP is a high-productivity, high-performance PA6 grade for film extrusion processes. Medium viscosity, unreinforced or reinforced Akulon grades are used for various injection molding and blow molding applications. Akulon® Ultraflow® is a high-productivity, high-performance PA6 family for molding processes. Key applications for Akulon: Automotive: Intake manifold, Engine, Powertrain, Airbag containers, Exterior trim, Interior trim, Electrical components and connectors Consumer durables: Power tools, Lawn and garden tools, Small appliances, Sports and leisure equipment, Furniture, Industrial Goods, Transportation E&E: Low voltage switch gear/power distribution, Lighting, Power connectors Film: Specialty and barrier films Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Akulon-Ultraflow-K-FHG0-Nylon-6-50-Glass-Reinforced-European-Grade-Dry.php

Physical Properties	Metric	English	Comments
Density	1.56 g/cc	0.0564 lb/in ³	ISO 1183
Water Absorption	4.5 %	4.5 %	Sim. to ISO 62
Moisture Absorption at Equilibrium	1.4 %	1.4 %	Humidity Absorption; Sim. to ISO 62
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	230 MPa	33400 psi	ISO 527-1/-2
Elongation at Break	2.5 %	2.5 %	ISO 527-1/-2
Tensile Modulus	16.5 GPa	2390 ksi	ISO 527-1/-2
Flexural Strength	350 MPa	50800 psi	ISO 178
Flexural Modulus	14.0 GPa	2030 ksi	ISO 178
Charpy Impact Unnotched	8.50 J/cm ²	40.5 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	9.00 J/cm ²	42.8 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179/1eA

Mechanical Properties	@Temperature -30.0 °C Metric	@Temperature -22.0 °F English	Comments
	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	10.0 µm/m-°C	5.56 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	50.0 µm/m-°C	27.8 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	220 °C	428 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.5	3.5	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	5.2	5.2	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dissipation Factor	0.0050	0.0050	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.015	0.015	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	500 V	500 V	IEC 60112

Descriptive Properties	Value	Comments
Heat stabilized or stable to heat	Yes	
Injection molding	Yes	
With Fillers	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China