

DSM Arnite® TV4 461 KL (PBT+PET)-GF30

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , PBT + PET Blend, Glass Filled

Material Notes:

30% Glass Reinforced, Heat Stabilized, UV Stabilized, Excellent Surface Properties

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Arnite-TV4-461-KL-PBTPET-GF30.php

Physical Properties	Metric	English	Comments
Density	1.55 g/cc	0.0560 lb/in ³	ISO 1183
Water Absorption	0.30 %	0.30 %	Sim. To ISO 62
Moisture Absorption	0.150 %	0.150 %	Sim. To ISO 62
Linear Mold Shrinkage, Flow	0.0032 cm/cm	0.0032 in/in	Sim. To ISO 294-4
Linear Mold Shrinkage, Transverse	0.011 cm/cm	0.011 in/in	Sim. To ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	130 MPa	18900 psi	ISO 527-1/-2
Elongation at Break	2.4 %	2.4 %	ISO 527-1/-2
Tensile Modulus	9.90 GPa	1440 ksi	ISO 527-1/-2
Charpy Impact Unnotched	4.50 J/cm ²	21.4 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	4.50 J/cm ²	21.4 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.900 J/cm ²	4.28 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.900 J/cm ²	4.28 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	40.0 µm/m-°C	22.2 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-1/-2
Deflection Temperature at 0.46 MPa (66 psi)	225 °C	437 °F	ISO 75-1/-2

Thermal Properties <small>Deflection Temperature at 1.8 MPa (104 psi)</small>	205 °C Metric	401 °F English	ISO 75-1/-2 Comments
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Dielectric Constant	3.9	3.9	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dissipation Factor	4.1	4.1	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	0.0015	0.0015	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	0.016	0.016	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	275 V	275 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China