

DSM Arnitel® XG5855 TPC-ET

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyester TPE , Polyester, TP

Material Notes:

Extrusion Grade

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Arnitel-XG5855-TPC-ET.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ISO 1183
Water Absorption	0.17 %	0.17 %	Sim. To ISO 62
Moisture Absorption	0.450 %	0.450 %	Sim. To ISO 62
Melt Flow	2.7 g/10 min @Load 2.16 kg, Temperature 230 °C	2.7 g/10 min @Load 4.76 lb, Temperature 446 °F	cm ³ /10min Melt Volume-flow Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	86 @Time 3.00 sec	86 @Time 0.000833 hour	ISO 868
Tensile Strength, Ultimate	8.50 MPa	1230 psi	ISO 527-1/-2
Tensile Stress	3.00 MPa @Strain 10.0 %	435 psi @Strain 10.0 %	ISO 527-1/-2
	4.40 MPa @Strain 100 %	638 psi @Strain 100 %	ISO 527-1/-2
Elongation at Break	350 %	350 %	ISO 527-1/-2
Tensile Modulus	0.0560 GPa	8.12 ksi	ISO 527-1/-2

Thermal Properties	Metric	English	Comments
Melting Point	172 °C	342 °F	10°C/min; ISO 11357-1/-3

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.90e+13 ohm-cm	1.90e+13 ohm-cm	IEC 60093
Dielectric Strength	21.0 kV/mm	533 kV/in	IEC 60243-1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China