

DSM Novamid® 2620A PA6/6T

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Extrusion

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Novamid-2620A-PA66T.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	dry; ISO 1183
Moisture Absorption	3.50 %	3.50 %	Sim. To ISO 62
Viscosity	70000 cP	70000 cP	
	@Shear Rate 10000 1/s, Temperature 240 °C	@Shear Rate 10000 1/s, Temperature 464 °F	
	70000 cP	70000 cP	
	@Shear Rate 10000 1/s, Temperature 260 °C	@Shear Rate 10000 1/s, Temperature 500 °F	
	70000 cP	70000 cP	
	@Shear Rate 10000 1/s, Temperature 280 °C	@Shear Rate 10000 1/s, Temperature 536 °F	
Viscosity Test	800000 cP	800000 cP	
	@Shear Rate 0.100 1/s, Temperature 280 °C	@Shear Rate 0.100 1/s, Temperature 536 °F	
	1.00e+6 cP	1.00e+6 cP	
	@Shear Rate 0.100 1/s, Temperature 260 °C	@Shear Rate 0.100 1/s, Temperature 500 °F	
	1.30e+6 cP	1.30e+6 cP	
	@Shear Rate 0.100 1/s, Temperature 240 °C	@Shear Rate 0.100 1/s, Temperature 464 °F	
Viscosity Test	183 cm ³ /g	183 cm ³ /g	Viscosity Number; ISO 307, 1157, 1628

Thermal Properties	Metric	English	Comments
Melting Point	205 °C	401 °F	10°C/min; ISO 11357-1/-3

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China