

## DSM Stanyl® 46HF5050 Nylon 46-50% Glass Reinforced (European and Asian Grade) (Cond)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Glass Fiber Reinforced

### Material Notes:

Stanyl is a high performance polyamide providing good performance and value across a broad range of automotive and electronic applications. Stanyl offers: Highest mechanical properties at high temperatures Excellent resistance to wear and low friction Outstanding flow for easy processing and exceptional design freedom Stanyl High Flow grades that match the best flowing LCPs while maintaining a high level of mechanical properties Key Applications: Automotive: Powertrain components, Charge-air coolers, EPS and ETC gears, Motor Sensors, Auto connectors, Chain tensioners E&E: Connectors, Microswitches, Bobbins, Memory modules, Motor components, Industrial, Specialty films and fibers, Consumer appliances Information provided by DSM.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DSM-Stanyl-46HF5050-Nylon-46-50-Glass-Reinforced-European-and-Asian-Grade-Cond.php](http://www.lookpolymers.com/polymer_DSM-Stanyl-46HF5050-Nylon-46-50-Glass-Reinforced-European-and-Asian-Grade-Cond.php)

Physical Properties	Metric	English	Comments
Density	1.87 g/cc	0.0676 lb/in <sup>3</sup>	(DAM); ISO 1183
Moisture Absorption at Equilibrium	1.1 %	1.1 %	Humidity Absorption (DAM); Sim. to ISO 62
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	DAM; ISO 294-4
	0.0070 cm/cm	0.0070 in/in	DAM; ISO 294-4

Thermal Properties	Metric	English	Comments
Melting Point	295 °C	563 °F	10°C/min (DAM); ISO 11357-1/-3
UL RTI, Electrical	140 °C	284 °F	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	140 °C	284 °F	UL746B
	@Thickness 0.750 mm	@Thickness 0.0295 in	
UL RTI, Mechanical with Impact	110 °C	230 °F	UL746B
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	125 °C	257 °F	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
UL RTI, Mechanical without Impact	120 °C	248 °F	UL746B
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	125 °C	257 °F	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	250 - 399 V	250 - 399 V	PLC 2; UL 746A

Descriptive Properties	Value	Comments
Flame Retardant	Yes	
Flame Retarding Agent	Yes	
Heat stabilized or stable to heat	Yes	
Injection molding	Yes	
Lubricants	Yes	
Platable	Yes	
Release Agent	Yes	
With Fillers	Yes	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China