

DSM Stanyl® TE250F6 (DAM) Nylon 46 30% Glass Reinforced, Heat Stabilized, Flame Retardant (North America)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Flame Retarded + Glass Fiber Reinforced

Material Notes:

Information provided by DSM Engineering Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TE250F6-DAM-Nylon-46-30-Glass-Reinforced-Heat-Stabilized-Flame-Retardant-North-America.php

Physical Properties	Metric	English	Comments
Density	1.68 g/cc	0.0607 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	1.6 %	1.6 %	50% RH / 23°C; Similar to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	180 MPa	26100 psi	ISO 527-1/-2
Elongation at Break	2.5 %	2.5 %	ISO 527-1/-2
Tensile Modulus	12.0 GPa	1740 ksi	ISO 527-1/-2
Charpy Impact Unnotched	5.00 J/cm ²	23.8 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 179/1eU
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	ISO 179/1eU
	0.900 J/cm ²	4.28 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 µm/m-°C	11.1 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	295 °C	563 °F	ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	290 °C	554 °F	ISO 75-1/-2
UL RTI, Electrical	140 °C	284 °F	UL746B

Thermal Properties	@Thickness 1.50 mm Metric	@Thickness 0.0591 in English	Comments
Flammability, UL94	V-0	V-0	
	@Thickness 0.350 mm	@Thickness 0.0138 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	IEC 60093
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60243-1
Comparative Tracking Index	250 V	250 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China