

DSM Stanyl® TS200B3 PA46-CF15

Category : Polymer , Thermoplastic , Nylon , Nylon 46

Material Notes:

15% Carbon Reinforced

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TS200B3-PA46-CF15.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	dry; ISO 1183
Moisture Absorption	3.15 %	3.15 %	Sim. To ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	110 MPa	16000 psi	cond; ISO 527-1/-2
	185 MPa	26800 psi	dry; ISO 527-1/-2
Elongation at Break	2.0 %	2.0 %	dry; ISO 527-1/-2
	4.0 %	4.0 %	cond; ISO 527-1/-2
Tensile Modulus	13.0 GPa	1890 ksi	dry; ISO 527-1/-2
Flexural Modulus	5.80 GPa	841 ksi	cond; ISO 178
	10.5 GPa	1520 ksi	dry; ISO 178
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	dry; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	25.0 µm/m-°C	13.9 µin/in-°F	dry; ISO 11359-1/-2
CTE, linear, Transverse to Flow	50.0 µm/m-°C	27.8 µin/in-°F	dry; ISO 11359-1/-2
Melting Point	295 °C	563 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	290 °C	554 °F	dry; ISO 75-1/-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China