

## DSM Stanyl® TS250F4D Nylon 46-40% Glass Reinforced (Asian Grade) (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Glass Fiber Reinforced

### Material Notes:

Stanyl is a high performance polyamide providing good performance and value across a broad range of automotive and electronic applications. Stanyl offers: Highest mechanical properties at high temperatures Excellent resistance to wear and low friction Outstanding flow for easy processing and exceptional design freedom Stanyl High Flow grades that match the best flowing LCPs while maintaining a high level of mechanical properties Key Applications: Automotive: Powertrain components, Charge-air coolers, EPS and ETC gears, Motor Sensors, Auto connectors, Chain tensioners E&E: Connectors, Microswitches, Bobbins, Memory modules, Motor components, Industrial, Specialty films and fibers, Consumer appliances Information provided by DSM.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DSM-Stanyl-TS250F4D-Nylon-46-40-Glass-Reinforced-Asian-Grade-Dry.php](http://www.lookpolymers.com/polymer_DSM-Stanyl-TS250F4D-Nylon-46-40-Glass-Reinforced-Asian-Grade-Dry.php)

Physical Properties	Metric	English	Comments
Density	1.56 g/cc	0.0564 lb/in <sup>3</sup>	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	150 MPa	21800 psi	ISO 527-1/-2
Elongation at Break	2.0 %	2.0 %	ISO 527-1/-2
Tensile Modulus	9.20 GPa	1330 ksi	ISO 527-1/-2
Charpy Impact, Notched	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 µm/m-°C	16.7 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	295 °C	563 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	290 °C	554 °F	ISO 75-1/-2
Flammability, UL94	V-0	V-0	IEC 60695-11-10
	@Thickness 0.750 mm	@Thickness 0.0295 in	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**