

DSM Stanyl® TS271P4 PA46-MF20

Category : Polymer , Thermoplastic , Nylon , Nylon 46

Material Notes:

20% Whisker Reinforced, Wear and Friction Modified

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TS271P4-PA46-MF20.php

Physical Properties	Metric	English	Comments
Density	1.47 g/cc	0.0531 lb/in ³	dry; ISO 1183
Moisture Absorption	2.90 %	2.90 %	Sim. To ISO 62
Linear Mold Shrinkage, Flow	0.0090 cm/cm	0.0090 in/in	Sim. To ISO 294-4
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	Sim. To ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	110 MPa	16000 psi	dry; ISO 527-1/-2
Elongation at Break	3.5 %	3.5 %	dry; ISO 527-1/-2
Tensile Modulus	7.00 GPa	1020 ksi	dry; ISO 527-1/-2
Flexural Modulus	6.00 GPa	870 ksi	dry; ISO 178
Charpy Impact, Notched	0.400 J/cm ² @Temperature 23.0 °C	1.90 ft-lb/in ² @Temperature 73.4 °F	dry; ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	295 °C	563 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	270 °C	518 °F	dry; ISO 75-1/-2
Flammability, UL94	HB @Thickness 0.790 mm	HB @Thickness 0.0311 in	dry; IEC 60695-11-10

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China