

DSM Stanyl® TW200F8 Nylon 46-40% Glass Reinforced (European Grade) (Cond)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Glass Fiber Reinforced

Material Notes:

Stanlyl is a high performance polyamide providing good performance and value across a broad range of automotive and electronic applications. Stanlyl offers: Highest mechanical properties at high temperatures Excellent resistance to wear and low friction Outstanding flow for easy processing and exceptional design freedom Stanlyl High Flow grades that match the best flowing LCPs while maintaining a high level of mechanical properties Key Applications: Automotive: Powertrain components, Charge-air coolers, EPS and ETC gears, Motor Sensors, Auto connectors, Chain tensioners E&E: Connectors, Microswitches, Bobbins, Memory modules, Motor components, Industrial, Specialty films and fibers, Consumer appliances Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TW200F8-Nylon-46-40-Glass-Reinforced-European-Grade-Cond.php

Physical Properties	Metric	English	Comments
Density	1.51 g/cc	0.0546 lb/in ³	(DAM); ISO 1183
Water Absorption	8.0 %	8.0 %	DAM; Sim. to ISO 62
Moisture Absorption at Equilibrium	2.2 %	2.2 %	Humidity Absorption (DAM); Sim. to ISO 62
Linear Mold Shrinkage, Flow	0.0050 cm/cm	0.0050 in/in	DAM; ISO 294-4
	0.011 cm/cm	0.011 in/in	DAM; ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	140 MPa	20300 psi	ISO 527-1/-2
Elongation at Break	6.0 %	6.0 %	ISO 527-1/-2
Tensile Modulus	8.00 GPa	1160 ksi	ISO 527-1/-2
Charpy Impact Unnotched	7.50 J/cm ² @Temperature -30.0 °C	35.7 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	9.50 J/cm ² @Temperature 23.0 °C	45.2 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	1.20 J/cm ² @Temperature -30.0 °C	5.71 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eA
	2.20 J/cm ² @Temperature 23.0 °C	10.5 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA
Tensile Creep Modulus, 1000 hours	5500 MPa	798000 psi	ISO 899-1

Mechanical Properties	Metric	English	Comments
Thermal Properties	Metric	English	Comments
Melting Point	295 °C	563 °F	10°C/min (DAM); ISO 11357-1/-3

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Dielectric Constant	4.7	4.7	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	16	16	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	20.0 kV/mm	508 kV/in	IEC 60243-1
Dissipation Factor	0.010	0.010	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	0.060	0.060	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	300 V	300 V	IEC 60112

Descriptive Properties	Value	Comments
Heat stabilized or stable to heat	Yes	
Injection molding	Yes	
Platable	Yes	
With Fillers	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China