

## DSM Stanyl® TW300 Nylon 46 (European and Asian Grade) (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Unreinforced

### Material Notes:

Stanyl is a high performance polyamide providing good performance and value across a broad range of automotive and electronic applications. Stanyl offers: Highest mechanical properties at high temperatures Excellent resistance to wear and low friction Outstanding flow for easy processing and exceptional design freedom Stanyl High Flow grades that match the best flowing LCPs while maintaining a high level of mechanical properties Key Applications: Automotive: Powertrain components, Charge-air coolers, EPS and ETC gears, Motor Sensors, Auto connectors, Chain tensioners E&E: Connectors, Microswitches, Bobbins, Memory modules, Motor components, Industrial, Specialty films and fibers, Consumer appliances Information provided by DSM.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DSM-Stanyl-TW300-Nylon-46-European-and-Asian-Grade-Dry.php](http://www.lookpolymers.com/polymer_DSM-Stanyl-TW300-Nylon-46-European-and-Asian-Grade-Dry.php)

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in <sup>3</sup>	ISO 1183
Water Absorption	13.5 %	13.5 %	Sim. to ISO 62
Moisture Absorption at Equilibrium	3.7 %	3.7 %	Humidity Absorption; Sim. to ISO 62
Viscosity Test	175 cm <sup>3</sup> /g	175 cm <sup>3</sup> /g	Viscosity Number
Linear Mold Shrinkage, Flow	0.020 cm/cm	0.020 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.020 cm/cm	0.020 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	100 MPa	14500 psi	ISO 527-1/-2
Elongation at Break	40 %	40 %	ISO 527-1/-2
Elongation at Yield	10 %	10 %	ISO 527-1/-2
Tensile Modulus	3.30 GPa	479 ksi	ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.900 J/cm <sup>2</sup>	4.28 ft-lb/in <sup>2</sup>	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	1.20 J/cm <sup>2</sup>	5.71 ft-lb/in <sup>2</sup>	ISO 179/1eA

Mechanical Properties	@Temperature 23.0 °C Metric	@Temperature 73.4 °F English	Comments
<b>Thermal Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
CTE, linear, Parallel to Flow	80.0 µm/m-°C @Temperature 20.0 °C	44.4 µin/in-°F @Temperature 68.0 °F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	100 µm/m-°C @Temperature 20.0 °C	55.6 µin/in-°F @Temperature 68.0 °F	ISO 11359-1/-2
Melting Point	295 °C	563 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	280 °C	536 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	190 °C	374 °F	ISO 75-1/-2
Vicat Softening Point	290 °C	554 °F	50°C/h 50N; ISO 306
Glass Transition Temp, Tg	75.0 °C	167 °F	Glass Transition Temperature (10°C/min); ISO 11357-1/-2
Flammability, UL94	V-2 @Thickness 0.750 mm	V-2 @Thickness 0.0295 in	IEC 60695-11-10
	V-2 @Thickness 1.60 mm	V-2 @Thickness 0.0630 in	IEC 60695-11-10
Oxygen Index	27 %	27 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Dielectric Constant	3.6 @Frequency 1e+6 Hz	3.6 @Frequency 1e+6 Hz	IEC 60250
	3.9 @Frequency 100 Hz	3.9 @Frequency 100 Hz	IEC 60250
Dielectric Strength	25.0 kV/mm	635 kV/in	IEC 60243-1
Dissipation Factor	0.00070 @Frequency 100 Hz	0.00070 @Frequency 100 Hz	IEC 60250
	0.0026 @Frequency 1e+6 Hz	0.0026 @Frequency 1e+6 Hz	IEC 60250
Comparative Tracking Index	400 V	400 V	IEC 60112

Descriptive Properties	Value	Comments
Heat stabilized or stable to heat	Yes	
Injection molding	Yes	
Platable	Yes	
Without Fillers	Yes	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China