

DSM Stanyl® TW371 (COND) Nylon 46 Heat Stabilized, PTFE Lubricated (North America)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Unreinforced

Material Notes:

Information provided by DSM Engineering Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TW371-COND-Nylon-46-Heat-Stabilized-PTFE-Lubricated-North-America.php

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in ³	(DAM); ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	50.0 MPa	7250 psi	ISO 527-1/-2
Elongation at Yield	>= 50 %	>= 50 %	Nominal; ISO 527-1/-2
Tensile Modulus	1.00 GPa	145 ksi	ISO 527-1/-2
Charpy Impact, Notched	3.00 J/cm ²	14.3 ft-lb/in ²	ISO 179/1eU

Thermal Properties	Metric	English	Comments
Melting Point	295 °C	563 °F	(DAM); ISO 11357-1/-3

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+7 ohm-cm	1.00e+7 ohm-cm	IEC 60093
Comparative Tracking Index	400 V	400 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China