

Daelim H&L Plavis-N DF Unfilled Aromatic Polyimide Bearing

Category : Polymer , Thermoset , Polyimide, TS

Material Notes:

Direct Formed. Plavis-N: Best physical properties, maximum electrical and thermal insulation, low out-gassing, superior radiation resistance. General Plavis information for all grades: PLAVIS polyimide has nitrogen bonded to 3 carbons is the critical part of the chain and imparts the plastic with remarkable features and benefits. PLAVIS is available as raw material or as molded parts, plates, and rods. PLAVIS isostatic molded rods have uniform properties in all directions. Properties: One of the highest temperature plastics in the world with a continuous operating temperature of 300?. Well suited for cryogenic conditions Retains high tensile strength and modulus even at high temperatures. Will not crack or creep under load. Lowest out-gassing of any plastic at 300?. Will not contaminate vacuum chamber process or products. Grades are available for use at 1 million psi-fpm PV limit with lubrication, 300,000 psi-fpm PV limit without lubrication. Stable friction level. Plavis-N is an ideal electrical and thermal insulator. Filled grades resistivity is tailorable. Machines like brass-tiny and intricate features can be produced without cracking. Can be lapped to mirror finish. Applications: Flat Panel Display/Solar Cells:: Drying oven (HP/CP, Baking, IR) Glass support pins, Glass holders, Rollers; Cleaning EUV roller, Bearing; PVD/CVD Insulation parts Insert, Clamp, Bush, Caps, Susceptor pin, Ball bearing etc.; Etcher Screw, bolts. and Others Probe unit, station parts Semiconductor: Wafer Processing Wafer clamp rings, Insulators, Screw & Fasteners, Vacuum pads, Alignment pins; Wafer handling, guides, and carriers, Vacuum pick up strips; IC handling & testing Die pick up collects, Test socket insulator General Industry: Hot runner system Seal caps, Insulators; Plasma cutting torches parts Swirl rings, Insulator, Caps.; Heat resistance materials Bottle grippers, Conveyor tips; Scientific consumable parts GC/Mass ferrules, HPLC valve rotors; Textile Machines Valve seat, Bearing, Shedder Bushing Automotive / Transportation: Transmissions Thrust Washers, Seal Rings, Valve Seats, Transmission Valve Balls, Check Valves; Electrical Motors Bushings, Washers, Thrust Plugs; Brakes Wear Pads, Valve Seats and Balls in ABS Systems; Fuel Systems Bushings, Seal Rings, Band Springs, Valve Seats; Turbo Chargers Ball Bearing Retainers, Wastegate Bushings; Vacuum Pump Vanes, Engine Belt Tensioners, Rubbing Blocks, Door Hinge Bushings, Gear Stick Rollers, Ignition Distributors, Constant Friction Pads for Split-Flywheels Aerospace/Aircraft: Compressor Variable Vane Bushings and Washers, Aircraft Fan Thrust Reverser, Fan Blade Wear Strips, Locking Insert Nut, Fuel Line Spacer, Reciprocating Shaft Seal for Jet Engine Afterburner Actuating System Information provided by Daelim H&L

Order this product through the following link:

http://www.lookpolymers.com/polymer_Daelim-HL-Plavis-N-DF-Unfilled-Aromatic-Polyimide-Bearing.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.34 g/cc	1.34 g/cc	ASTM D792
Moisture Absorption	0.900 - 1.10 %	0.900 - 1.10 %	50% RH; ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	75.0 - 90.0	75.0 - 90.0	ASTM D785
Tensile Strength, Ultimate	79.4 MPa	11500 psi	ASTM D1708
	39.2 MPa	5690 psi	ASTM D1708
	@Temperature 260 °C	@Temperature 500 °F	

Elongation at Break Mechanical Properties	8.50 % Metric	8.50 % English	ASTM D1708 Comments
	7.50 % @Temperature 260 °C	7.50 % @Temperature 500 °F	ASTM D1708
Flexural Strength	84.3 MPa	12200 psi	ASTM D790
	46.1 MPa @Temperature 260 °C	6690 psi @Temperature 500 °F	ASTM D790
Flexural Modulus	2.55 GPa	370 ksi	ASTM D790
	1.422 GPa @Temperature 260 °C	206.2 ksi @Temperature 500 °F	ASTM D790
Compressive Strength	24.5 MPa @Strain 1.00 %	3550 psi @Strain 1.00 %	ASTM D695
	112.8 MPa @Strain 10.0 %	16360 psi @Strain 10.0 %	ASTM D695
Compressive Modulus	2.403 GPa	348.5 ksi	ASTM D695
Izod Impact, Notched	0.588 J/cm	1.10 ft-lb/in	ASTM D256
Coefficient of Friction	0.340	0.340	PV=10 kg/cm ² · m/sec (0.98 Mpa·m/sec)

Thermal Properties	Metric	English	Comments
CTE, linear	50.0 µm/m-°C @Temperature 23.0 - 260 °C	27.8 µin/in-°F @Temperature 73.4 - 500 °F	ASTM D696
Maximum Service Temperature, Air	300 °C	572 °F	Continuous
	370 °C	698 °F	50% tensile strength reduction at 200 hours
Deflection Temperature at 1.8 MPa (264 psi)	360 °C	680 °F	
Decomposition Temperature	520 °C	968 °F	50wt% reduction after 239 min
	614 °C	1140 °F	short term
Flammability, UL94	V-0	V-0	
Oxygen Index	55.0 %	55.0 %	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	Metric 1.00e+16 - 1.00e+18 ohm-cm	English 1.00e+16 - 1.00e+18 ohm-cm	Comments
Surface Resistance	1.00e+14 - 1.00e+16 ohm	1.00e+14 - 1.00e+16 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China