

Daikin DAI-EL G-751 Fluoroelastomer Copolymer, Bisphenol Curable Grade, 66% Fluorine Content

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Offers minimal compression set and excellent sealing. The copolymer type offers good compression set characteristics. Features: General purpose with excellent metal bonding and compression set. Information provided by Daikin Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Daikin-DAI-EL-G-751-Fluoroelastomer-Copolymer-Bisphenol-Curable-Grade-66-Fluorine-Content.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.85 g/cc	1.85 g/cc	at 25°C
Mooney Viscosity	30 @Temperature 121 °C	30 @Temperature 250 °F	ML 1+10

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	72	72	Peak value, at 25°C
Tensile Strength at Break	15.1 MPa	2190 psi	
Tensile Strength, Yield	5.00 MPa @Strain 100 %	725 psi @Strain 100 %	
Elongation at Break	190 %	190 %	
Tear Strength	19.6 kN/m	112 pli	at 25°C
Compression Set	8.0 %	8.0 %	70 hours at 25°C
	5.0 % @Temperature 100 °C	5.0 % @Temperature 212 °F	70 hours
	11 % @Temperature 175 °C	11 % @Temperature 347 °F	70 hours
	18 % @Temperature 200 °C	18 % @Temperature 392 °F	70 hours

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-18.0 °C	-0.400 °F	TR test, TR10
	-13.0 °C	8.60 °F	Gehman torsion test, T10

Thermal Properties	-9.00 °C Metric	15.8 °F English	TR test TR70 Comments
	-6.00 °C	21.2 °F	Gehman torsion test, T2
Brittleness Temperature	-17.0 °C	1.40 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	170 °C	338 °F	Cure Measuring Temperature
Cure Time	2.80 min	0.0467 hour	Curelastmeter

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China