

Daikin DAI-EL G-901 Fluoroelastomer Terpolymer, Peroxide Curable Grade, 71% Fluorine Content

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Offers excellent chemical and steam resistance. Offers good mechanical characteristics. Features: Excellent solvent resistance. Information provided by Daikin Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Daikin-DAI-EL-G-901-Fluoroelastomer-Terpolymer-Peroxide-Curable-Grade-71-Fluorine-Content.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.84 g/cc	1.84 g/cc	at 25°C
Mooney Viscosity	48 @Temperature 121 °C	48 @Temperature 250 °F	ML 1+10

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	Peak value, at 25°C
Tensile Strength at Break	22.0 MPa	3190 psi	
Tensile Strength, Yield	2.80 MPa @Strain 100 %	406 psi @Strain 100 %	
Elongation at Break	320 %	320 %	
Tear Strength	19.6 kN/m	112 pli	at 25°C
Compression Set	13 %	13 %	70 hours at 25°C
	12 % @Temperature 100 °C	12 % @Temperature 212 °F	70 hours
	18 % @Temperature 175 °C	18 % @Temperature 347 °F	70 hours
	32 % @Temperature 200 °C	32 % @Temperature 392 °F	70 hours

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-8.00 °C	17.6 °F	TR test, TR10
	-5.00 °C	23.0 °F	Gehman torsion test, T10

Thermal Properties	-2.00 °C Metric	28.4 °F English	TR test TR70 Comments
	-1.30 °C	29.7 °F	Gehman torsion test, T2
Brittleness Temperature	-26.0 °C	-14.8 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	160 °C	320 °F	Cure Measuring Temperature
Cure Time	3.00 min	0.0500 hour	Curelastmeter

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China