

Daikin NEOFロン ND-4GY FEP Dispersion, Gray

Category : Polymer , Thermoplastic , Fluoropolymer , FEP , Fluorinated Ethylene Propylene (FEP), Molded/Extruded

Material Notes:

NEOFロン FEP dispersions are fine-powder suspension. Two types are available: water based and organic solvent based. Since FEP has good flowability when melted, a continuous, pinhole-free film can be obtained. Description: Aqueous. Major Uses: Coating. Information provided by Daikin Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Daikin-NEOFロン-ND-4GY-FEP-Dispersion-Gray.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	at 25°C
Solids Content	39 %	39 %	
Oxygen Transmission	320 cc-mm/m ² -24hr-atm	812 cc-mil/100 in ² -24hr-atm	at 25°C
Nitrogen Transmission	104 cc-mm/m ² -24hr-atm	263 cc-mil/100 in ² -24hr-atm	at 25°C
Viscosity	3.0 - 7.5 cP	3.0 - 7.5 cP	

Thermal Properties	Metric	English	Comments
Flammability, UL94	V-0	V-0	FEP Component
Oxygen Index	>= 95 %	>= 95 %	FEP Component

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.0 - 2.2	2.0 - 2.2	FEP Component; ASTM D150
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dissipation Factor	2.0 - 2.2	2.0 - 2.2	FEP Component; ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dissipation Factor	0.00010 - 0.00030	0.00010 - 0.00030	FEP Component

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China