

Daikin NEOFLON NF-0250 FEP Film

Category: Polymer, Film, Thermoplastic, Fluoropolymer, FEP, Fluorinated Ethylene Propylene (FEP), Molded/Extruded

Material Notes:

NEOFLON FEP films are a high performance film made from NEOFLON FEP resin and have superior reliability and retention of their properties. NEOFLON FEP is applicable in such diversified fields as electrical, chemical, food, and pharmaceutical industries. Information provided by Daikin Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Daikin-NEOFLON-NF-0250-FEP-Film.php

Physical Properties	Metric	English	Comments
Oxygen Transmission	320 cc-mm/m²-24hr- atm	812 cc-mil/100 in²- 24hr-atm	at 25°C
Nitrogen Transmission	104 cc-mm/m²-24hr- atm	263 cc-mil/100 in²- 24hr-atm	at 25°C
Thickness	254 microns	10.0 mil	

Mechanical Properties	Metric	English	Comments
Coefficient of Friction	0.040 - 0.060	0.040 - 0.060	

Thermal Properties	Metric	English	Comments
Flammability, UL94	V-0	V-0	
Oxygen Index	>= 95 %	>= 95 %	

Optical Properties	Metric	English	Comments
Transmission, Visible	92 - 95 %	92 - 95 %	
IR Transmittance	95 - 98 %	95 - 98 %	
UV Transmittance	91 - 92 %	91 - 92 %	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.0 - 2.2	2.0 - 2.2	ASTM D150
Dielectric Constant	@Frequency 1000 Hz	@Frequency 1000 Hz	
	2.0 - 2.2	2.0 - 2.2	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dissipation Factor	0.00010 - 0.00030	0.00010 - 0.00030	



Descriptive Properties	Value	Comments
Roll Length	80 mm	
Roll Weight	50 kg	
Roll Width	1250 mm	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China