

Denka REOMER G G3010 Thermoplastic Elastomer, For Extrusion

Category : Polymer , Thermoplastic , Elastomer , TPE

Material Notes:

Essentially a thermoplastic elastomer with the characteristics of PVC resin and rubber, with excellent rubber-like elasticity. Offers excellent rubbery characteristics, such as permanent compressive distortion, rebound elasticity, etc. compared to soft PVC, and excellent bending strength and ozone resistance compared to rubber.

Applications: Automotive components]door moldingsweather-stripsglass run channelsside bumpersgasketsmud flapshead restsarm restssteering wheelstrimshift bar bootspedal pads[Construction material, manufacturing article home electric, appliance components]gasketsairtight materialscontainer packingpacking for vacuum cleanershosetubes[For electric wire]appliance cordscabtire

Order this product through the following link:

http://www.lookpolymers.com/polymer_Denka-REOMER-G-G3010-Thermoplastic-Elastomer-For-Extrusion.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	JIS-Z-8807
Evaporation Loss	2.3 %	2.3 %	JIS-A-5756

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58	58	JIS-K-6301
Tensile Strength at Break	12.753 MPa	1849.7 psi	JIS-K-6723
Elongation at Break	420 %	420 %	JIS-K-6723
100% Modulus	0.005886 GPa	0.8537 ksi	JIS-K-6723
Resilience	32	32	JIS-K-6301

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-38.0 °C	-36.4 °F	JIS-K-6723

Descriptive Properties	Value	Comments
Heating: Retention Rate of Elongation, %	99	100°C x 120 hrs
Heating: Retention Rate of Tensile Strength, %	99	100°C x 120 hrs
Oil Resistance: Retention of Tensile Strength, %	83	JIS-K-6723
Oil Resistance: Retention Rate of Elongation, %	75	JIS-K-6723

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China