

Denka REOMER G G5074 Thermoplastic Elastomer, For Extrusion

Category : Polymer , Thermoplastic , Elastomer , TPE

Material Notes:

Essentially a thermoplastic elastomer with the characteristics of PVC resin and rubber, with excellent rubber-like elasticity. Offers excellent rubbery characteristics, such as permanent compressive distortion, rebound elasticity, etc. compared to soft PVC, and excellent bending strength and ozone resistance compared to rubber. Applications: Automotive components, door moldings, weather-strips, glass run channels, side bumpers, gaskets, mud flaps, head rests, arm rests, steering wheel, trim, shift bar, boots, pedal pads. Construction material, manufacturing article, home electric, appliance components, gaskets, airtight materials, container packing, packing for vacuum cleaners, hoses, tubes. For electric wire, appliance cords, cable tire.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Denka-REOMER-G-G5074-Thermoplastic-Elastomer-For-Extrusion.php

Physical Properties	Metric	English	Comments
Density	1.26 g/cc	0.0455 lb/in ³	JIS-Z-8807
Evaporation Loss	9.0 %	9.0 %	JIS-A-5756

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	74	74	JIS-K-6301
Tensile Strength at Break	19.62 MPa	2846 psi	JIS-K-6723
Elongation at Break	390 %	390 %	JIS-K-6723
100% Modulus	0.006867 GPa	0.9960 ksi	JIS-K-6723
Resilience	28	28	JIS-K-6301
Compression Set	54 %	54 %	JIS-K-6301

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-51.0 °C	-59.8 °F	JIS-K-6723

Descriptive Properties	Value	Comments
Bending Strength, Times, JIS-K-6301	over 100k	
Heating: Retention Rate of Elongation, %	90	100°C x 120 hrs
Heating: Retention Rate of Tensile Strength, %	110	100°C x 120 hrs
Oil Resistance: Retention of Tensile Strength, %	98	JIS-K-6723
Oil Resistance: Retention Rate of Elongation, %	88	JIS-K-6723

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China