

Devcon Sprayable Ceramic™ Epoxy

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Adhesive

Material Notes:

Precision Repair EpoxyComments: A sprayable ceramic-reinforced composite that can be sprayed in a manner similar to high-solid paints. Ideal for protecting pumps, paper machines, stacks, pump pads, steel frames and tanks. Excellent chemical resistance. Spray 15 to 33 mils in one pass. Use standard airless equipment. Available in red and blue.Data provided by Ellsworth Adhesives.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Devcon-Sprayable-Ceramic-Epoxy.php

Physical Properties	Metric	English	Comments
Density	1.69 g/cc	0.0610 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	87	87	ASTM D2240
Tensile Strength, Ultimate	26.2 MPa	3800 psi	ASTM D638
Modulus of Elasticity	6.21 GPa	900 ksi	In Tension; ASTM D638
Flexural Yield Strength	55.2 MPa	8000 psi	ASTM D790
Compressive Yield Strength	105 MPa	15200 psi	ASTM D695
Adhesive Bond Strength	13.8 MPa	2000 psi	Adhesive tensile shear strength; ASTM D1002

Thermal Properties	Metric	English	Comments
CTE, linear	34.0 μm/m-°C	18.9 μin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	0.803 W/m-K	5.57 BTU-in/hr-ft ² -°F	ASTM C177
Maximum Service Temperature, Air	177 °C	350 °F	Operating Temperature
Shrinkage	0.20 %	0.20 %	During Cure; ASTM D2566

Electrical Properties	Metric	English	Comments
Dielectric Constant	38.7	38.7	ASTM D150
Dielectric Strength	15.0 kV/mm	382 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Processing Temperature	21.1 °C	70.0 °F	

Processing Properties	Metric	English	Comments
Pot Life	@Temperature 23.9 °C	@Temperature 75.0 °F	

Descriptive Properties	Value	Comments
Coverage per gal.	108 ft ²	at 15 mils thick
Mix Ratio by Volume	7.1 to 2.1 to 1	resin:hardener:thinner
Mix Ratio By Weight	14 to 2.5 to 1	resin:hardener:thinner

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China