

## Diamond Polymers ABS 7600B (ELG)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Impact Grade, Molded

### Material Notes:

Description: Blow Molding Grade, Extra High Impact, Low Gloss  
Information provided by Diamond Polymers, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Diamond-Polymers-ABS-7600B-ELG.php](http://www.lookpolymers.com/polymer_Diamond-Polymers-ABS-7600B-ELG.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
Melt Flow	0.80 g/10 min	0.80 g/10 min	Procedure A Condition G; ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	3.0 g/10 min	3.0 g/10 min	Procedure A Condition I; ASTM D1238
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	102	102	ASTM D785
Tensile Strength, Yield	40.7 MPa	5900 psi	chs 2 in/min; ASTM D638
Flexural Modulus	1.90 GPa	275 ksi	Tangent, chs 0.05 in/min; ASTM D790
Izod Impact, Notched	4.27 J/cm	8.00 ft-lb/in	bar; ASTM D256
	@Thickness 3.17 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	0.125 in bar Unannealed/Conditioned 48 hours at 23°C; ASTM D648
	96.1 °C	205 °F	0.125 in bar Annealed 4 hours at 80°C; ASTM D648
Vicat Softening Point	104 °C	220 °F	0.125 inch, 1 Kg; ASTM D1525
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Optical Properties	Metric	English	Comments
Gloss	6.0 %	6.0 %	Specular Gloss, Texture MT, 11030

Optical Properties	Metric	English	Geometry 60"; ASTM D523 Comments
<b>Processing Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Middle Barrel Temperature	200 - 220 °C	392 - 428 °F	
Mold Temperature	40.0 - 60.0 °C	104 - 140 °F	Higher mold temperature provides a product with excellent surface finishing and less residual stress.
Drying Temperature	80.0 - 85.0 °C	176 - 185 °F	
Dry Time	2 - 4 hour	2 - 4 hour	
Injection Pressure	4.83 - 6.21 MPa	700 - 900 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China