

Diamond Polymers ABS VP-11 ELG

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Unreinforced, Flame Retardant

Material Notes:

Description: Extrusion Grade, Low Gloss, Flame Retardant Information provided by Diamond Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Diamond-Polymers-ABS-VP-11-ELG.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0090 cm/cm	0.0040 - 0.0090 in/in	ASTM D955
Melt Flow	0.90 g/10 min	0.90 g/10 min	Procedure A Condition G; ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	10.1 g/10 min	10.1 g/10 min	Procedure A; ASTM D1238
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	96	96	ASTM D785
Tensile Strength, Yield	39.14 MPa	5677 psi	chs 2 in/min; ASTM D638
Flexural Modulus	2.04 GPa	296 ksi	Tangent, chs 0.05 in/min; ASTM D790
Izod Impact, Notched	4.00 J/cm	7.50 ft-lb/in	bar; ASTM D256
	@Thickness 3.17 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	72.2 °C	162 °F	0.125 in bar Unannealed/Conditioned 48 hours at 23°C; ASTM D648
Vicat Softening Point	100.5 °C	212.9 °F	0.125 inch, 1 Kg; ASTM D1525
Flammability, UL94	V-0	V-0	All Color
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	V-0	V-0	All Color
	@Thickness 2.50 mm	@Thickness 0.0984 in	
	5VA	5VA	All Color
	@Thickness 3.00 mm	@Thickness 0.118 in	

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Gloss	42 %	42 %	60° View Angle; ASTM D523

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	200 - 220 °C	392 - 428 °F	
Mold Temperature	40.0 - 60.0 °C	104 - 140 °F	Higher mold temperature provides a product with excellent surface finishing and less residual stress.
Drying Temperature	80.0 - 85.0 °C	176 - 185 °F	
Dry Time	2 - 4 hour	2 - 4 hour	
Injection Pressure	4.83 - 6.21 MPa	700 - 900 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China