

Diamond Polymers ASA S170

Category : Polymer , Thermoplastic , ASA Polymer , Acrylonitrile/Styrene/Acrylate (ASA), Unreinforced, Molded

Material Notes:

Description: ASA Weatherable Polymer, Injection Molding Grade, High Impact Information provided by Diamond Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Diamond-Polymers-ASA-S170.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.07 g/cc	1.07 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955
Melt Flow	7.0 g/10 min @Load 10.0 kg, Temperature 220 °C	7.0 g/10 min @Load 22.0 lb, Temperature 428 °F	Procedure A; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	93	93	ASTM D785
Tensile Strength, Yield	40.0 MPa	5800 psi	chs 2 in/min; ASTM D638
Flexural Modulus	2.07 GPa	300 ksi	Tangent, chs 0.05 in/min; ASTM D790
Izod Impact, Notched	3.74 J/cm @Thickness 3.17 mm, Temperature 23.0 °C	7.00 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	bar; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	0.125 in bar Unannealed/Conditioned 48 hours at 23°C; ASTM D648
	93.9 °C	201 °F	0.125 in bar Annealed 4 hours at 80°C; ASTM D648
Vicat Softening Point	88.9 °C	192 °F	0.125 inch, 1 Kg; ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China