

Diamond Polymers ASA T-115

Category : Polymer , Thermoplastic , ASA Polymer , Acrylonitrile/Styrene/Acrylate (ASA), Unreinforced, Molded

Material Notes:

Description: ASA Weatherable Polymer, Injection Molding Grade, High Heat Resistance Information provided by Diamond Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Diamond-Polymers-ASA-T-115.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.07 g/cc	1.07 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	ASTM D955
Melt Flow	0.30 g/10 min	0.30 g/10 min	Procedure A Condition G; ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	1.1 g/10 min	1.1 g/10 min	Procedure A Condition I; ASTM D1238
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	101	101	ASTM D785
Tensile Strength, Yield	44.1 MPa	6400 psi	chs 2 in/min; ASTM D638
Flexural Modulus	2.25 GPa	327 ksi	Tangent, chs 0.05 in/min; ASTM D790
Izod Impact, Notched	1.01 J/cm	1.90 ft-lb/in	bar; ASTM D256
	@Thickness 3.17 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	96.1 °C	205 °F	0.125 in bar Unannealed/Conditioned 48 hours at 23°C; ASTM D648
	111 °C	232 °F	0.125 in bar Annealed 4 hours at 80°C; ASTM D648
Vicat Softening Point	107 °C	225 °F	0.125 inch, 1 Kg; ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China