

Diamond Polymers ASAPC 6040 UV Stabilized

Category : Polymer , Thermoplastic , ASA Polymer , Polycarbonate (PC) , Polycarbonate/ASA Alloy, Unreinforced

Material Notes:

Information Provided by Diamond Polymers, Inc. & Network Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Diamond-Polymers-ASAPC-6040-UV-Stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955
Melt Flow	35 g/10 min @Load 5.00 kg, Temperature 265 °C	35 g/10 min @Load 11.0 lb, Temperature 509 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	48.7 MPa	7060 psi	chs 2.0 in/min; ASTM D638
Flexural Modulus	2.019 GPa	292.8 ksi	chs 0.05 in/min; ASTM D790
Izod Impact, Notched	5.87 J/cm @Thickness 3.17 mm	11.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	123 °C @Load 1.00 kg, Thickness 3.17 mm	253 °F @Load 2.20 lb, Thickness 0.125 in	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China