

## Diamond Polymers DIAMALLOY 761 ABS/PC Alloy, Non-Halogen Flame Retardant with 5% PTFE

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

### Material Notes:

Information Provided by Diamond Polymers, Inc. & Network Polymers, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Diamond-Polymers-DIAMALLOY-761-ABSPC-Alloy-Non-Halogen-Flame-Retardant-with-5-PTFE.php](http://www.lookpolymers.com/polymer_Diamond-Polymers-DIAMALLOY-761-ABSPC-Alloy-Non-Halogen-Flame-Retardant-with-5-PTFE.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955
Melt Flow	3.6 g/10 min	3.6 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	11.2 g/10 min	11.2 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	54.9 MPa	7960 psi	chs 2.0 in/min; ASTM D638
Elongation at Yield	4.3 %	4.3 %	chs 2.0 in/min; ASTM D638
Flexural Modulus	2.487 GPa	360.7 ksi	chs 0.05 in/min; ASTM D790
Izod Impact, Notched	1.335 J/cm	2.501 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	108 °C	226 °F	ASTM D1527
	@Load 1.00 kg, Thickness 3.17 mm	@Load 2.20 lb, Thickness 0.125 in	
Flammability, UL94	V-0	V-0	
	@Thickness 1.59 mm	@Thickness 0.0625 in	
	V-0	V-0	
	@Thickness 3.17 mm	@Thickness 0.125 in	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**