

Diamond Polymers NPP30-0500 GF30 BLACK HOMOPOLYMER 30% Glass Filled Black Homopolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Information Provided by Diamond Polymers, Inc. & Network Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Diamond-Polymers-NPP30-0500-GF30-BLACK-HOMOPOLYMER-30-Glass-Filled-Black-Homopolymer-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ASTM D792
Melt Flow	6.5 g/10 min @Load 2.16 kg, Temperature 230 °C	6.5 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	85.0 MPa	12300 psi	chs 0.2 in/min; ASTM D638
Elongation at Yield	3.0 %	3.0 %	chs 0.2 in/min; ASTM D638
Flexural Modulus	5.27 GPa	764 ksi	ASTM D790
Izod Impact, Notched	0.800 J/cm @Thickness 3.17 mm	1.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	155 °C	311 °F	0.125";; ASTM D648

Descriptive Properties	Value	Comments
Glass Content (%)	30	ASTM D2584

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China