

## Diamond Polymers PC 0814 Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

Information Provided by Diamond Polymers, Inc. &amp; Network Polymers, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Diamond-Polymers-PC-0814-Polycarbonate.php](http://www.lookpolymers.com/polymer_Diamond-Polymers-PC-0814-Polycarbonate.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955
Melt Flow	8.0 g/10 min @Load 1.20 kg, Temperature 300 °C	8.0 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	62.0 MPa	8990 psi	chs 2.0 in/min; ASTM D638
Flexural Modulus	2.277 GPa	330.3 ksi	chs 0.05 in/min; ASTM D790
Izod Impact, Notched	7.47 J/cm @Thickness 3.17 mm	14.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	129 °C	264 °F	0.125";; ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China