

## Diamond Polymers SBS 1031 Clear Styrene Butadiene Copolymer

Category : Polymer , Thermoplastic , Styrene-Butadiene , Styrene-Butadiene Copolymer, SBC

**Material Notes:**

Information Provided by Diamond Polymers, Inc. &amp; Network Polymers, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Diamond-Polymers-SBS-1031-Clear-Styrene-Butadiene-Copolymer.php](http://www.lookpolymers.com/polymer_Diamond-Polymers-SBS-1031-Clear-Styrene-Butadiene-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.01 g/cc	1.01 g/cc	ASTM D792
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	Flow Direction; ASTM D955
Melt Flow	9.0 g/10 min @Load 5.00 kg, Temperature 200 °C	9.0 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.6 MPa	4000 psi	chs 2.0 in/min; ASTM D638
Flexural Strength	37.2 MPa	5400 psi	chs 0.05 in/min; ASTM D790
Flexural Modulus	1.654 GPa	239.9 ksi	chs 0.05 in/min; ASTM D790
Izod Impact, Notched	0.232 J/cm @Thickness 3.17 mm	0.435 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	64.2 °C	148 °F	0.125";; ASTM D648
Vicat Softening Point	90.7 °C @Load 1.00 kg, Thickness 3.17 mm	195 °F @Load 2.20 lb, Thickness 0.125 in	ASTM D1525

Optical Properties	Metric	English	Comments
Haze	<= 4.0 %	<= 4.0 %	
Yellow Index	<= 8.4 %	<= 8.4 %	BAM 1015
Transmission, Visible	90 %	90 %	clear; thickness not quantified

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China