

Domo 1040RC Polypropylene Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Information provided by Domo.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Domo-1040RC-Polypropylene-Homopolymer.php

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in ³	ISO 1183
Melt Flow	23 g/10 min	23 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Modulus	2.00 GPa	290 ksi	ISO 527-2
Izod Impact, Notched (ISO)	1.30 kJ/m ²	0.619 ft-lb/in ²	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	2.50 kJ/m ²	1.19 ft-lb/in ²	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	DSC; ISO 3146
Vicat Softening Point	100 °C	212 °F	B50 (50N); ISO 306
	157 °C	315 °F	A50 (10N); ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China