

Domo 1101M Polypropylene Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Information provided by Domo.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Domo-1101M-Polypropylene-Homopolymer.php

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in ³	ISO 1183
Melt Flow	9.5 g/10 min	9.5 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Modulus	1.50 GPa	218 ksi	ISO 527-2

Thermal Properties	Metric	English	Comments
Melting Point	163 °C	325 °F	DSC; ISO 3146
Vicat Softening Point	90.0 °C	194 °F	B50 (50N); ISO 306
	154 °C	309 °F	A50 (10N); ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China