

## Domo 2600PC Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

**Material Notes:**

Information provided by Domo.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Domo-2600PC-Polypropylene-Copolymer.php](http://www.lookpolymers.com/polymer_Domo-2600PC-Polypropylene-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in <sup>3</sup>	ISO 1183
Melt Flow	15 g/10 min	15 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Modulus	1.00 GPa	145 ksi	ISO 527-2
Izod Impact, Notched (ISO)	3.50 kJ/m <sup>2</sup>	1.67 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	4.00 kJ/m <sup>2</sup>	1.90 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	5.00 kJ/m <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature 0.000 °C	@Temperature 32.0 °F	
	12.0 kJ/m <sup>2</sup>	5.71 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	163 °C	325 °F	ISO 3146
Vicat Softening Point	56.0 °C	133 °F	B50 (50N); ISO 306
	142 °C	288 °F	A50 (10N); ISO 306

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China