

Domo Domamid® 34 Polyamide 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

DOMAMID® 34 are Polyamide 6 pellets with a higher viscosity produced from Caprolactam by polymerization. Applications: Standard quality for production of monofilaments and films. Information provided by Domo

Order this product through the following link:

http://www.lookpolymers.com/polymer_Domo-Domamid-34-Polyamide-6.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	
Volatiles	<= 0.60 %	<= 0.60 %	Extractables; BUP - 06
Apparent Bulk Density	0.600 - 0.800 g/cc	0.0217 - 0.0289 lb/in ³	
Viscosity Measurement	3.36 - 3.5 @Temperature 20.0 °C	3.36 - 3.5 @Temperature 68.0 °F	1% Solution in 96% H2SO4; BUP - 02

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.060 %	<= 0.060 %	BUP - 05

Descriptive Properties	Value	Comments
Chip Number	ca. 80 to 100/g	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China