

## Dow 6D20 Polypropylene Resin

Category : Polymer , Thermoplastic , Polypropylene (PP)

**Material Notes:**

DOW 6D20 is intended for use in film and extrusion blow molding processes. It is especially suited for multilayered, barrier bottles. Information provided by DowDow Announced Sale of Global Polypropylene Business to Braskem in July 2011.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-6D20-Polypropylene-Resin.php](http://www.lookpolymers.com/polymer_Dow-6D20-Polypropylene-Resin.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ASTM D792
Melt Flow	1.9 g/10 min @Temperature 230 °C	1.9 g/10 min @Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.9 MPa	3900 psi	molded and tested in accordance with ASTM D 4101; ASTM D638
Elongation at Yield	10 %	10 %	molded and tested in accordance with ASTM D 4101; ASTM D638
Flexural Modulus	1.024 GPa	148.5 ksi	1% Secant; molded and tested in accordance with ASTM D 4101; ASTM D790A
Izod Impact, Notched	0.587 J/cm	1.10 ft-lb/in	molded and tested in accordance with ASTM D 4101; ASTM D256A
	0.267 J/cm @Temperature -20.0 °C	0.500 ft-lb/in @Temperature -4.00 °F	molded and tested in accordance with ASTM D 4101; ASTM D256A

Thermal Properties	Metric	English	Comments
Melting Point	148 °C	298 °F	Dow Method (DSC)
Deflection Temperature at 0.46 MPa (66 psi)	83.9 °C	183 °F	unannealed; molded and tested in accordance with ASTM D 4101; ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China