

Dow AFFINITY™ GA 1950 Polyolefin Plastomer (POP)

Category : Polymer , Thermoplastic , Polyolefin

Material Notes:

AFFINITY™ GA 1950 Polyolefin Plastomer (POP) is produced via INSITE™ Technology from Dow Plastics. This product can be used in applications such as polymer modification (i.e. flow enhancement and property enhancement), masterbatch / additive carrier, and hot melt adhesives. Information provided by Dow

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-AFFINITY-GA-1950-Polyolefin-Plastomer-POP.php

Physical Properties	Metric	English	Comments
Density	0.874 g/cc	0.0316 lb/in ³	ASTM D792
Brookfield Viscosity	17000 cP @Temperature 177 °C	17000 cP @Temperature 350 °F	ASTM D1084
Collected Volatile Condensable Material	<= 0.15 %	<= 0.15 %	Modified for polyolefins. Change in temperature used to 100°C ± 3 and the amount of sample to 20 grams.; ASTM D3030

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1.76 MPa	255 psi	ASTM D638
Elongation at Break	185 %	185 %	ASTM D638

Thermal Properties	Metric	English	Comments
Melting Point	70.0 °C	158 °F	Dow Method
Glass Transition Temp, Tg	-57.0 °C	-70.6 °F	Dow Method

Optical Properties	Metric	English	Comments
Gardner Color Number	1.0	1.0	ASTM D3417

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China