

Dow ASPUN™ 6830A Linear Low-Density Polyethylene (LLDPE)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

ASPUN™ 6830A Fiber Grade Resin: Suggested Optimum Process: Staple Typical Application: Yarn & Biocomponent Fibers Information provided by Dow

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-ASPUN-6830A-Linear-Low-Density-Polyethylene-LLDPE.php

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in ³	ASTM D792
Melt Flow	18 g/10 min @Load 2.16 kg, Temperature 190 °C	18 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	125 °C	257 °F	Dow Method (DSC)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China