

## Dow Corning 200® 1000 CST FLUID

Category : Fluid

**Material Notes:**

100% active, 1000 cSt, polydimethylsiloxane polymer. Information provided by Dow Corning

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-Corning-200-1000-CST-FLUID.php](http://www.lookpolymers.com/polymer_Dow-Corning-200-1000-CST-FLUID.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.971 g/cc @Temperature 25.0 °C	0.971 g/cc @Temperature 77.0 °F	
Viscosity Measure	1000 cSt	1000 cSt	kinetic/kinematic
Surface Tension	21.2 dynes/cm	21.2 dynes/cm	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.159 W/m-K	1.10 BTU-in/hr-ft <sup>2</sup> -°F	
Maximum Service Temperature, Air	200 °C	392 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	
Pour Point	-50.0 °C	-58.0 °F	
Flash Point	>= 100 °C	>= 212 °F	closed cup
	>= 321 °C	>= 610 °F	open cup

Optical Properties	Metric	English	Comments
Refractive Index	1.403	1.403	

Descriptive Properties	Value	Comments
Hydrophobic	yes	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China