

Dow Corning 733 GLASS & METAL SEALANT

Category : Polymer , Adhesive , Thermoset , Silicone , Silicone, RTV, Adhesive/Sealant Grade

Material Notes:Conventional acetoxo RTV sealant with adhesion promoter
Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-733-GLASS-METAL-SEALANT.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|----------|
| Specific Gravity | 1.03 g/cc | 1.03 g/cc | |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|----------|---------|----------|
| Hardness, Shore A | 25 | 25 | |
| Tensile Strength, Ultimate | 2.31 MPa | 335 psi | |
| Elongation at Break | 500 % | 500 % | |

| Processing Properties | Metric | English | Comments |
|-----------------------|----------------------|----------------------|----------|
| Cure Time | 1440 min | 24.0 hour | |
| | @Temperature 22.0 °C | @Temperature 71.6 °F | |
| Shelf Life | 30.0 Month | 30.0 Month | |

| Descriptive Properties | Value | Comments |
|------------------------|----------|----------|
| Appearance | clear | |
| Color | Aluminum | |
| | Black | |
| | White | |
| Water Resistant | yes | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China