

Dow Corning FZ-2233

Category : Other Engineering Material , Additive/Filler for Polymer

Material Notes:

Its primary function is to produce water-in-silicone and water-in-silicone and oil emulsions with a creamy and rich appearance but leaving a light, non greasy after feel on the skin. The addition level can be as low as 2% leaving a lot of flexibility for the oil phase composition. The emulsions have also a very small particle size (average around 1 micron) resulting in highly stable emulsions at elevated temperatures but also through several freeze thaw cycles. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-FZ-2233.php

| Physical Properties | Metric | English | Comments |
|---------------------|----------------------|----------------------|-------------------|
| Specific Gravity | 0.990 g/cc | 0.990 g/cc | |
| | @Temperature 25.0 °C | @Temperature 77.0 °F | |
| Viscosity Measure | 5000 cSt | 5000 cSt | Kinetic/Kinematic |

| Thermal Properties | Metric | English | Comments |
|--------------------|-----------|-----------|------------|
| Flash Point | >= 198 °C | >= 388 °F | Closed cup |

| Optical Properties | Metric | English | Comments |
|--------------------|--------|---------|----------|
| Refractive Index | 1.42 | 1.42 | |

| Processing Properties | Metric | English | Comments |
|-----------------------|------------|------------|----------|
| Shelf Life | 24.0 Month | 24.0 Month | |

| Descriptive Properties | Value | Comments |
|-------------------------|-------|----------|
| Nonvolatile Content (%) | 97 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China