

Dow Corning MOLYKOTE® 33 EXTREME LOW TEMPERATURE BEARING GREASE, LIGHT

Category : Fluid , Lubricant , Silicone Base

Material Notes:

Phenyl-methyl silicone grease for extreme low temperatures Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-MOLYKOTE-33-EXTREME-LOW-TEMPERATURE-BEARING-GREASE-LIGHT.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------------------------------|------------------------------------|----------|
| Specific Gravity | 0.970 g/cc @Temperature 25.0 °C | 0.970 g/cc @Temperature 77.0 °F | |

| Mechanical Properties | Metric | English | Comments |
|---------------------------------------|----------|-----------------|----------|
| Four Ball Extreme Pressure, Weld Load | 122.3 kg | 269.7 lb (mass) | |
| Penetration P(60), 1/10 mm | 320 | 320 | |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|----------|----------|
| Maximum Service Temperature, Air | 204 °C | 399 °F | |
| Minimum Service Temperature, Air | -73.0 °C | -99.4 °F | |
| Dropping Point | 226 °C | 439 °F | |

| Processing Properties | Metric | English | Comments |
|-----------------------|------------|------------|----------|
| Shelf Life | 60.0 Month | 60.0 Month | |

| Descriptive Properties | Value | Comments |
|------------------------|--------------|----------|
| Color | white | |
| NLGI Number | 1 | |
| Thickening System | lithium soap | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China